

CERTAINTEED® REGULAR DRYWALL PANEL

Job Name _____

Contractor _____

Date _____

Products Specified _____

PRODUCT DESCRIPTION

CertainTeed Regular Drywall Panel is an interior drywall panel that consists of a non-combustible gypsum core enclosed in ivory colored face paper and liner back paper. Long edges are slightly tapered, allowing joints to be reinforced and concealed with joint tape and joint compound.

BASIC USES

CertainTeed Regular Drywall Panel is used for interior walls and ceilings in standard residential or commercial applications. It can be used for new construction or renovations over wood or steel framing. It is typically nailed or screwed to studs spaced 16" (406 mm) or 24" (610 mm) o.c., but can be applied by laminating or with the use of an adhesive.

1/4" (6.4 mm) Regular Drywall Panel is recommended as an additional layer in double-layer wood or steel-framed partitions, and as a face layer for use over old wall and ceiling surfaces.

3/8" (9.5 mm) Regular Drywall Panel is recommended in single or double-layer wood or steel-framed wall and ceilings, as an additional layer for use over old wall and ceiling surfaces.

ADVANTAGES

- Uniformly flat, attractive appearance.
- High edge hardness.
- No wavy edges, warps, bows or deformities.
- Uniform high-strength cores eliminate crumbling, cracking.
- Edge tapers consistent to form perfect joints.
- Excellent thermal barrier and sound attenuation qualities.
- GREENGUARD® Gold Certified.

INSTALLATION

LIMITATIONS

- Exposure to continuous moisture or extreme temperatures should be avoided. Not recommended for continuous exposure to temperatures exceeding 125°F (52°C).
- 1/4" (6.4 mm) Regular Drywall Panel is not recommended for ceiling application.
- Ceiling framing spacing should not exceed 16" (406 mm) o.c.
- Wall framing spacing should not exceed 16" (406 mm) o.c..
- Store indoors and off ground surface.
- Panels should be stacked flat with care taken to prevent sagging or damage to edges, ends and surfaces.
- Storing panel lengthwise leaning against the framing is not recommended.
- Panels should be carried, not dragged, to place of installation to prevent damaging finished edges.
- Cutting and scoring should be done from the face side.
- In cold weather or during joint finishing, temperatures within the enclosure should stay within the range of 50° to 95°F (10° to 35°C) and with sufficient ventilation to carry off excess moisture.



PRODUCT DATA

| PROPERTIES | REGULAR DRYWALL PANELS |
|------------|--------------------------------------------------------------------------------------------------------------------------------------|
| Thickness | 1/4" (6.4 mm), 3/8" (9.5 mm) |
| Width | 4' (1220 mm) |
| Length | 8' (2440 mm) |
| Weight | 1/4" (6.4 mm) - 1.13 lb/ft ² (5.5 kg/m ²) 3/8" (9.5 mm) - 1.25 lb/ft ² (6.1 kg/m ²) |
| Edges | Tapered |
| Packaging | Two pieces per bundle, face-to-face and end-taped. |

Custom lengths may be available on special order. Consult your CertainTeed sales representative.

TECHNICAL DATA

| APPLICABLE STANDARDS AND REFERENCE | |
|------------------------------------|-----------------------------------------|
| Product Standard | ASTM C1396 |
| Installation Guidelines | ASTM C840 / GA-216 |
| Finishing Guidelines | ASTM C840 / GA-214 |
| Code References | International Building Code (IBC) |
| Code References | International Residential Code (IRC) |
| Code References | National Building Code of Canada (NBCC) |

| PHYSICAL PROPERTIES | 1/4" (6.4 MM) REGULAR | 3/8" (9.5 MM) REGULAR | TEST METHOD |
|---------------------------------------------------|--------------------------------------------------|--------------------------------------------------|----------------------------------|
| Nominal Width | 4' (1220 mm) | 4' (1220 mm) | - |
| Standard Lengths | 8' (2440 mm) | 8' (2440 mm) | - |
| Face Surface | Paper | Paper | - |
| Weight - lb/ft ² (kg/m ²) | 1.13 lb/ft ² (5.5 kg/m ²) | 1.25 lb/ft ² (6.1 kg/m ²) | - |
| Edge Profile | Tapered | Tapered | |
| Surface Burning Characteristics - Flame Spread | 15 (15) | 15 (15) | ASTM E84 / UL 723 (CAN/ULC-S102) |
| Surface Burning Characteristics - Smoke Developed | 0 (0) | 0 (0) | ASTM E84 / UL 723 (CAN/ULC-S102) |
| Surface Burning Characteristics | Class A | Class A | ASTM E84 / UL 723 (CAN/ULC-S102) |
| Nail Pull | ≥ 36 lbf (160 N) | ≥ 56 lbf (249 N) | ASTM C473 (Method B) |
| Core Hardness - End | ≥ 11 lbf (49 N) | ≥ 11 lbf (49 N) | ASTM C473 (Method B) |
| Core Hardness - Edge | ≥ 11 lbf (49 N) | ≥ 11 lbf (49 N) | ASTM C473 (Method B) |
| Flexural Strength - Parallel | ≥ 16 lbf (71 N) | ≥ 26 lbf (116 N) | ASTM C473 (Method B) |
| Flexural Strength - Perpendicular | ≥ 46 lbf (205 N) | ≥ 77 lbf (343 N) | ASTM C473 (Method B) |
| Humidified Deflection | N/A | ≤ 1-7/8" inch (48mm) | ASTM C473 |

DECORATION

CertainTeed® Regular Drywall Panel accepts most types of paints, texture and wall covering materials. The surface shall be primed with a full-bodied latex primer before applying a final decorative material. This will equalize the suction between the joint compounds and the paper surface. For best painting results, all surfaces, including joint compound, should be clean, dust-free and not glossy. If glossy paints are used, a thin skim coat of compound over the entire surface, Level 5 finish, is recommended to reduce highlighting or joint photographing. This method is also recommended for areas of critical sidelighting of natural or artificial light sources. A sealer application under wallpaper or other wall covering is also recommended so the panel surface will not be damaged if the covering is subsequently removed during redecorating. Joint treatment must be thoroughly dry before proceeding with primer-sealer application and final decoration.

BIM/CAD INFORMATION

The BIM and CAD UL fire rated assemblies and sound assemblies can be found on CertainTeed's BIM and CAD Design Studio at bimlibrary.saint-gobain.com/certainteed. CertainTeed's BIM and CAD Design Studio provides BIM and CAD details to many UL

fire rated assemblies and sound assemblies in easy to view experience. Plus, downloadable Revit and DWG and PDF CAD Details are available.

SUSTAINABILITY

Sustainable documentation, including recycled content, EPD's, HPD's, VOC Certifications, can be found at saintgobain.ecomedes.com.

NOTICE

The information in this document is subject to change without notice. CertainTeed assumes no responsibility for any errors that may inadvertently appear in this document.

For Fire Resistance, no warranty is made other than conformance to the standard under which the assembly was tested. Minor discrepancies may exist in the values of ratings, attributable to changes in materials and standards, as well as differences between testing facilities. Assemblies are listed as "combustible" (wood framing) and "noncombustible" (concrete and/or steel construction).

USGBC® and the related logo are trademarks owned by the U.S. Green Building Council and are used with permission.



The Health Product Declaration® logo is a trademark or service mark of Health Product Declaration Collaborative, Inc., in the United States and in other countries and is being used herein under license.



CertainTeed

CEILINGS • DECKING • FENCE • GYPSUM • INSULATION • RAILING • ROOFING • SIDING • TRIM
20 Moores Road, Malvern, PA 19355 800-233-8990 certainteed.com